



ZINKY-12 INORGANIC ZINC RICH PRIMER 77

TECHNICAL DATA SHEET

PRODUCT DESCRIPTION

Zinky-12 Inorganic Zinc Rich Primer 77 is a two-pack, solvent-based coating composed of ethyl silicate and zinc dust. It is suitable for use on steel as a primer for high performance systems and as a single treatment coating for a variety of marine environment. It prevents corrosion and provides excellent resistance to weathering, abrasion, impact, heat and many solvents.

The level of zinc dust by weight present in the dried film conforms to SSPC-Paint 20 (Level 2). The type of zinc dust used complies with ASTM D 520 (Type II). It has been tested for Slip Coefficient and Creep Resistance, using ASTM A490 bolts and meets Class B requirements by RCSC Specification for Structural Joints Using High-Strength Bolts (Appendix A).

INTENDED USE

Recommended coating systems based on Zinky-12 Inorganic Zinc Rich Primer 77 are suitable for severe corrosive environments such as offshore platforms, petrochemical complexes, gas and petroleum refineries, pulp and paper mills and corrosive chemical plants.

Provide excellent corrosion protection of properly prepared steel exposed up to temperature of 540°C, with suitable top coat. Continuous dry temperature resistance of Zinky-12 is 400°C if left untopcoated.

GENERAL PROPERTIES

Colour	: Grey
Gloss Level	: Matt
Volume Solids, %	: 58 ± 2 %
Specific Gravity	: 2.18 kg/l (Mixed)
Flash point	: Base: 22°C Mix: 22°C
VOC	: 556 g/L (EPA Method 24)
Typical Thickness	: 50 – 75 µm dry film : 86 – 129 µm wet film

Remark

For high temperature systems, the thickness of Zinky-12 should be restricted to 50 µm dry film.

SURFACE PREPARATION

All surfaces should be clean, dry and free from contamination. The surface should be assessed and treated in accordance with ISO 8504. Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

Abrasive blast cleaning to Sa 2½ (ISO 8501-1:2007). For optimum performance, blast cleaned to SSPC-SP10 with a surface profile of 50 – 75 microns (2 – 3 mils). If oxidation has occurred between the blasting and



ZINKY-12 INORGANIC ZINC RICH PRIMER 77

TECHNICAL DATA SHEET

application of this product, the surface should be re-blasted to the specified visual standard. Surface defect revealed by the blast cleaning process should be ground, filled or treated in the appropriate manner.

Damaged Area

Damage area should be prepared with abrasive blast cleaning to Sa 2½ (ISO 8501-1:2007). After the surface preparation, repair the damaged area using Zinky-12.

Zinky-12 Inorganic Zinc Rich Primer 77 should be applied over a surface that is dry and free from dirt, grease, oil and other contaminants and must be applied within the overcoating intervals specified (refer to application section for details).

Other Surfaces

The coating should not be used on other substrates. Please contact your local Nippon Paint office for more information.

CONDITION DURING APPLICATION

Avoid paint application when the temperature is below 5°C above 45°C. The temperature of steel surface must be a minimum 3°C above dew point of surrounding air. To achieve the best film performance, curing temperature should be kept at 10°C above and humidity 65% above. When humidity is less than 65%, spray water to ensure curing.

APPLICATION GUIDE

Mixing Ratio	: Base : Hardener = 0.685 : 1 (by weight) 4.5 : 1 (by volume) Add zinc powder (Hardener) into Base and mix thoroughly before use.
Pot Life	: 25°C 4 hours
Theoretical Coverage	: 11.6 m ² /litre at 50 µm DFT 7.73 m ² /litre at 75 µm DFT
Thinner	: Zinky-2000 Thinner

APPLICATION METHOD

Conventional Air and airless spray are recommended for application. Brush and roller are recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness. Avoid mud cracking.



ZINKY-12 INORGANIC ZINC RICH PRIMER 77

TECHNICAL DATA SHEET

APPLICATION DETAILS

Airless Spray : Tip Size : 0.015" – 0.023"
: Pressure at nozzle : 120 – 150 kg/cm²

Typical Thickness : 50 – 75 µm dry film
: 86 – 129 µm wet film

Remark

For high temperature systems, the thickness of Zinky-12 should be restricted to 50 µm dry film.

Drying Time : Substrate Temperature : 25°C 40°C
: Surface Dry : 10 mins 5 mins
: Through Dry : 2 hrs 1 hr
: Cured * : 4.5 hrs 2 hrs
: Dry to recoat (min)* : 4.5 hrs 2 hrs
: Dry to recoat (max)** : Extended

Remarks: All zinc salts should be removed prior to overcoating

* Depends on humidity conditions

** Where an "extended" overcoating time is stated, consult Nippon Paint Protective Coatings for recommended surface preparation to achieve optimal intercoat adhesion.

It is recommended that prior to overcoating a solvent rub test to ASTM D4752 should be undertaken. A value of 4 indicates a satisfactory degree of cure for overcoating purposes.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

RECOMMENDED PAINTING SYSTEM

The following coating systems are recommended for Zinky-12 Inorganic Zinc Rich Primer 77:

Intermediate

- Hi-Pon 20-04 STE 80
- Hi-Pon 20-04 STE IM 80
- Hi-Pon 30-02 Epoxy MIO 80
- Hi-Pon 30-03 Epoxy Midcoat 80

Topcoat

- Hi-Pon 40-02 Epoxy Top Coat
- Hi-Pon 40-04 Epoxy Top Coat



ZINKY-12 INORGANIC ZINC RICH PRIMER 77

TECHNICAL DATA SHEET

- Hi-Pon 50-01 Polyurethane Top Coat
- Hi-Pon 50-03 Polyurethane Top Coat
- Hi-Floro 6738 Fluorocarbon Top Coat

High Temperature Top Coat

- Hi-Pon 600HT Top Coat

For the choice of coating system for different application, refer to the product brochure or contact Nippon Paint for professional recommendation.

PACKAGING

Unit	Base		Hardener	
	Weight	Container Size	Weight	Container Size
10.6 KG (4.86 L)	4.3 KG	5 L	6.3 KG	5 L

STORAGE

Shelf life : Part A: 6 months (25°C)
Part B: 12 months (25°C)

Subject to re-inspection thereafter. Higher temperature during storage may reduce the shelf life and may lead to gelling in the tin. Frequent temperature cycles may also shorten the shelf life.

Store in tightly closed container in a dry, cool and well ventilated space, keep away from sources of heat and ignition.

SAFETY PRECAUTION

- This product is intended for use of professional applicators. Refer to the safety information display on the container and in the safety data sheet (SDS) before using the product.
- Use this product in well-ventilated area, avoid skin contact, spillage on the skin should immediately be removed with suitable cleanser, soap and water.
- Eye should be well flush with water and seek for medical attention immediately upon contact with this product.
- During the application, naked flame, welding operation and smoking is not allowed. Adequate ventilation should be provided.
- If you have any doubt regarding the suitability of use, refer to Nippon Paint for further advice.

DISCLAIMER

The information in this data sheet is given to the best of Nippon Paint's knowledge and practical experience. Users may consult with Nippon Paint on the general suitability of the product for their needs and



ZINKY-12 INORGANIC ZINC RICH PRIMER 77

TECHNICAL DATA SHEET

specific application practices though it remains each user's responsibility to determine the suitability of the product for the user's particular use. The condition of the substrate and application are not within Nippon Paint's control. Therefore no implied conditions, warranties or other terms will apply to the Product. Nippon Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will Nippon Paint be liable to the user for any kind of loss (whether direct or indirect) even if Nippon Paint was previously advised of it. In line with Nippon Paint's policy for continuous development, Nippon Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user's responsibility to check with Nippon Paint for the latest version of this data sheet. This data sheet has been translated into various languages. In the event of any inconsistency, the English version shall prevail.