



## TEST RESULTS HI-VINYL 1101 WASH PRIMER

Ref : Test Result/TR-216  
Established: 13-Feb-2019  
Updated: -

Test Items	Test Methods	Results
Surface Dry @ 25°C	ASTM D1640-14	5 mins
Hard Dry @ 25°C	ASTM D1640-14	10 mins
Cross-Cut Adhesion (Substrate: Mild Steel)	ISO 2409	Classification 0
Cross-Cut Adhesion (Substrate: Stainless Steel)	ISO 2409	Classification 0
Cross-Cut Adhesion (Substrate: Electro-Galvanized)	ISO 2409	Classification 1
Cross-Cut Adhesion (Substrate: Aluminum Plate)	ISO 2409	Classification 1
Min. Overcoatability	ISO 16927	1 hours
Max. Overcoatability	ISO 16927	3 months
Salt Spray Test (Substrate: Blasted Carbon Steel)	ISO 9227	Passed 168 hours
Humidity Test (Substrate: Blasted Carbon Steel)	ISO 6270-1	Passed 168 hours
Natural Exposure (Substrate: Blasted Carbon Steel)	ISO 2810	Passed 6 months

### REMARK:

1. Paint system on which test was performed: 1 coat of 20 µm (DFT)
2. Surface Preparation before testing: Sa. 2.5 blasted carbon steel
3. Test Performance results were obtained in a controlled lab environments specified in test method.

### NIPPON PAINT (SINGAPORE) CO PTE LTD

1, First Lok Yang Road, Jurong, Singapore 629728. Tel: 6268 5355 Fax: 6264 1603

Co Reg No. 196200138N

[www.nipponpaint.com.sg](http://www.nipponpaint.com.sg)

A MEMBER OF THE NIPSEA GROUP

### DISCLAIMER:

The above information is given to the best of Nippon Paint's knowledge and practical experience. It has been compiled based on data obtained under laboratory test conditions. Actual performance will depend upon the conditions in which the product is used. Users may consult with Nippon Paint on the general suitability of the product for their needs and specific application practices though it remains each user's responsibility to determine the suitability of the product for the user's particular use. Nippon Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will Nippon Paint be liable to the user for any kind of loss (whether direct or indirect) even if Nippon Paint was previously advised of it.