

**TECHNICAL DATA SHEET FOR
AQUA WOODGUARD**

DESCRIPTION	:	Aqua WoodGuard is a quick drying water-based coating, specially formulated using Advanced Polyurethane Dispersion (PUD) technology. The coating protects timber surfaces from the harmful effects of UV ray and enhances the natural beauty of wood grains with a long lasting finish. It has good durability and flexibility, suitable for decks and outdoor furniture
TYPE	:	One pack water-based PUD paint for interior and exterior use
COLOUR	:	Transparent colours as per colour card
FINISH	:	Gloss and Soft Matt
USES	:	Suitable for all types of new wood surfaces and those previously painted with a transparent wood film such as stair railing, fences, door, frame, furniture, parquet flooring and deck etc
FEATURES	:	<ul style="list-style-type: none">• Good UV and weather resistance• Excellent water repellent property• Good dirt resistance• Good stain resistance• Good resistance to fungus and mold• Good flow and levelling• Water-based• Easy to apply and clean• Non- toxic, does not contain heavy metal
APPLICATION DATA		
METHOD	:	Brush
THEORETICAL COVERAGE	:	Approximately 13 m ² / litre per coat (depend on surface porosity)
DILUTION	:	Ready for use. If necessary, dilute with 5% clean water to improve ease of application
SURFACE PREPARATION	:	<ul style="list-style-type: none">• New or unpainted wood surfaces :<ol style="list-style-type: none">a) Surface must be clean, dry and free from grease, paint, wax, dirt and other contaminants before paintingb) Clean off mould, algae, lichen and moss with a wire brushc) Smooth bare wood surface to be painted using grade #60 or #80 sandpaper, working in the direction of the grain before dusting off

AQUA WOODGUARD

- d) If necessary, fill the wood grains with appropriate filler and smooth with sandpaper (grade #150 or #180)
- e) Wood must be relatively dry and moisture content should not exceed 20% based on Sovereign Moisture Master before painting.
- f) Allow the paint to dry thoroughly before applying next coat
- g) Should fibre be observed, dry sand lightly before subsequent coat

Sanding between individual coats is necessary. Use grade #360 or #400 for sanding topcoat

- **Previously Painted Wood Surfaces :**

- a) If the previous paint film is in sound condition and without wax, smoothen it with sandpaper. Clean off and dry
- b) For old paint which is in sound condition and without wax, smoothen it with sandpaper. Clean off and dry
- c) Otherwise, remove all unstable paint film, dust, oil, wax and other foreign matters
- d) Particular care is necessary on previously waxed surfaces and thorough mechanical sanding is recommended to remove all wax. Presence of wax on substrates will affect the drying and adhesion of the paint coating

DRYING TIME : Surface dry - 45 minutes at 30 °C
 Hard dry - 3 hours at 30 °C

OVERCOATING TIME : Minimum 4 hours under normal conditions

RECOMMENDED PAINTING SYSTEM : 2 to 3 coats of Aqua WoodGuard until a satisfactory wood finish is obtained

CLEANING : All equipment should be cleaned with water immediately after use

GENERAL INFORMATION

SOLID CONTENT : 33.0 ± 2.0 % by weight (gloss, varies from colour to colour)
 31.0 ± 2.0 % by weight (sheen, varies from colour to colour)

SPECIFIC GRAVITY : 1.03 ± 2.0 % kg / litre (gloss and sheen)

PACKING : 1 litre and 5 litres

STORAGE : Store in a tightly sealed container in a cool, dry place

SHELF LIFE : Up to 12 months in a tightly sealed container

AQUA WOODGUARD

PRECAUTION

: New wool brushes used for application should be soaked in detergent solution for 3 – 5 minutes and rinsed with clean water before use. Avoid painting when the temperature is below 10 °C or above 35 °C or when the humidity is over 85 %. Ensure good ventilation during application and drying of paint. Ensure adequate protection and avoid direct contact on sensitive skin, eyes, etc

Refer to the product Safety Data Sheet for more information

The information given is intended to give a description of the product performance under specific test conditions. Nevertheless, we cannot assume any responsibility for the use of it since circumstances under which the products are applied in practice are subjected to many variations. We reserve the right to alter the given data without notice.

Enquiries / Contact Details

: **Customer Service**
6265 5355 (Main Line)
6264 1603 (Fax)
www.nipponpaint.com.sg