

Marine Paint Manual

Reference No. : 12 - 17

Issue Date: March 2013 (ES)

ECOLOFLEX SPC 400 HyB

Patented copolymer technology (Copper silyl acrylate copolymer) which ensures long term and stable self-smoothing effect which makes the fresh active coating surface constantly exposed to seawater, resulting in excellent antifouling performance. It is specially designed for coastal vessels.

Suitable Use	Coastal vessels (Medium to high speed)		
Type	Copper silyl acrylate copolymer (Tin-free / Self-smoothing / Hydrolysis / High solid)		
Colour	Chery V Plum V		
Gloss	Semi Gloss		
Volume Solids	52 ± 2% (ISO3233:1998)		
Typical Dry Film Thickness	80 ~ 150 µm		
Approx. Wet Film Thickness	154 ~ 288 µm		
Theoretical Coverage	5.40 m ² / L (100 µm)		
Drying Time	Surface Dry	1 hour (5°C)	40 minutes (20°C) 30 minutes (30°C)
	Dry Hard	3 hours (5°C)	1 hour (20°C) 40 minutes (30°C)
Interval before Overcoating (by self)	Min.	6 hours (5°C)	4 hours (20°C) 3 hours (30°C)
	Max.	- (5°C)	- (20°C) - (30°C)
Interval before Immersion	Min	18 hours (5°C)	12 hours (20°C) 10 hours (30°C)
Thinner	NIPPON MARINE THINNER 300 (0 ~ 5%, by weight)		
Application Method	Airless Spray	Tip range	0.69 ~ 0.84 mm
		Fan range	60 ~ 75°
		Output pressure above 150 kg / cm ²	
	Brush / Roller	For touching up small areas only	
Package	16L Package may vary from country to country.		
Japan Local Brand	ECOLOFLEX SPC 400 HyB		
Flash Point	24° C		
Surface Preparation	All surfaces to be coated should be clean, dry and free from contamination. High pressure fresh water wash and remove all oil / grease, soluble contaminants and other foreign matters.		
Safety	Take precautions to avoid skin and eye contact (i.e. gloves, goggles, face masks, barrier creams etc.) Proper ventilation and protective measures must be provided during applications and drying period to keep solvent vapour concentrations within safe limits. Prior to use, obtain, consult and follow the MSDS for this product concerning health and safety information.		



Marine Paint Manual

ECOLOFLEX SPC 400 HyB

Issue Date: March 2013 (ES)

< Note >

- 1) The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.
- 2) Use NIPPON MARINE THINNER 300 to wash painting appliances, hoses and guns before and after use.
- 3) The declaration letter of Tin-free Antifouling Paint would not be issued if mixed with the other antifouling paints product or another chemical products.
- 4) Store the paints in paint store.