

TECHNICAL DATA SHEET FOR

## FLOOR-PRO 317 SL NOVALAC EPOXY FINISH

FLOOR-PRO 317 SL NOVALAC EPOXY FINISH is a two-component, self-smoothing Novalac epoxy resin floor finish applied at 1~2mm. It provides a dust free, seamless, chemical and abrasion resistance glossy finishing

### FEATURES

- Solvent-free, low odour
- Hygienic, easy to clean and maintenance
- High chemical resistance to wide range of chemicals
- Good abrasion resistant against medium traffic and trolley movement
- Hard wearing floors finish
- Complied with BS6920 requirement

### APPLICATION AREAS

- Used for dry processing areas where the floor is subjected to trolley, pallet truck and fork lift traffic
- Idea to use at laboratories, electronic and clean rooms, automotive assembly, aircraft hangar, pharmaceutical, printing pulp paper, mills, refineries and other industrial plants sectors where chemical resistance are required

### PHYSICAL PROPERTIES

Chemical Composition	Solvent-free self-smoothing novalac epoxy
Colour	As per standard colours
Density, mixed	1.40 ± 0.05 g/cm <sup>3</sup> @ 28°C
Solid Content, mixed	100%

### PERFORMANCE DATA

Adhesive strength	>2.0 N/mm <sup>2</sup> (Concrete failure)
Compressive strength	55 N/mm <sup>2</sup> @ 28 days
Flexural strength	35 N/mm <sup>2</sup>
Tensile Strength	25 N/mm <sup>2</sup>
Shore D hardness	75 ~ 82
Temperature Resistance	Up to 100°C
Water Permeability	Nil-Karsten test (impermeable)
Taber Abrasion Wear Index	37 mg / 1000 revolutions / 1 Kg (ASTM D 4060)
Growth of Aquatic Microorganisms	< 2.39 mg/L (BS 6920: Part 1:2000)

\*Conditions such as installation process, inappropriate maintenance, short and long-term wear and use as well as surface contaminants (wet or dry) affects the slipperiness of flooring materials. To meet slip resistance requirement for wet conditions and/or surface contaminants (wet or dry), appropriate textured or anti-slip floor systems are recommended. Please contact Nippon Paint for further details and specifications.

\*\*The final floor finish shall follow the profile of the concrete, therefore appropriate levelling compound is recommended to treat the undulating surface.

### APPLICATION GUIDE

Mixing Ratio (by weight)	Part A : Part B 4 : 1
Recommended Thickness	1 – 2 mm per coat
Theoretical coverage	1.4 Kg/m <sup>2</sup> /mm
Recoating time	

Pot Life (Working time)	30 mins @ 28°C			
Curing time	15°C	25°C	32°C	
	Foot traffic (hrs)	24	20	18
	Light traffic (hrs)	36	30	24
	Exposure to chemicals (days)	10	7	7
Substrate Temperature relative to dew point	≥ 3°C			
Recommended application temperature range	Minimum 5°C Maximum 40°C			
Relative Humidity	< 85%			

### SUBSTRATE REQUIREMENT

- Concrete or screed substrate should be a minimum of 25 N/mm<sup>2</sup> and adhesive pull off strength of 1.5 N/mm<sup>2</sup>, free from laitance, dust and other contamination.
- The substrate should be dried up to 85% RH as per BS8204 and free from rising damp and ground water pressure.

### SURFACE PREPARATION

- Concrete substrate must be clean, free of laitance and contaminants.
- The concrete substrate must be dry and waterproofed against negative ground water pressure.
- Appropriate moisture barrier at 2 mm thickness is recommended if the substrate moisture > 4%.
- In the event of high substrate moisture > 6%, it is recommended to apply a 5 mm thickness high compressive strength anti-osmosis epoxy mortar as moisture tolerance system.
- Allow to cure over-night before the application of subsequent painting system. Prepare the concrete substrate surface by captive shot blasting, scarifying or mechanical grinding. Repair damaged area and patch up cracks and holes using a patching compound. Cut 5mmX5mm grooves around the perimeter of the floor and at end points (eg: plinth, column, drains etc.)

### APPLICATION METHOD

#### Applying Primer

- Apply FLOOR-PRO 106 SF EPOXY PRIMER at 0.25 Kg/m<sup>2</sup> for sealing the substrate porosity

#### Applying FLOOR-PRO 317 SL NOVALAC EPOXY FINISH

- FLOOR-PRO 317 SL NOVALAC EPOXY FINISH is only allowed to overcoat onto FLOOR-PRO 106 SF EPOXY PRIMER within 8-14 hours cured
- Stir Part A mix for 30 seconds by using a suitable electrical stirrer (with 750 watt high power mixer), then pour all of Part B (Hardener) and mix both liquid parts thoroughly for 2 minutes until fully homogenous

### PACKAGING

Components	PART A (BASE)	PART B (HARDENER)
TOTAL 5 Kg	4	1
TOTAL 10 Kg	8	2

**STORAGE AND SHELF LIFE**

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care. (Unopened and in good condition temperature 10°C to 30°C)

Components	PART A (BASE)	PART B (HARDENER)
Months	12	12

**SAFETY PRECAUTION**

- This product is intended for use by professional applicators. Refer to the safety information display on the container and in the safety data sheet (SDS) before using the product.
- Use this product in well-ventilated area, avoid skin contact, spillage on the skin should immediately be removed with suitable cleanser, soap and water.
- Eye should be well flushed with water and seek for medical attention immediately upon contact with this product.
- During the application, naked flame, welding operation and smoking is not allowed. Adequate ventilation should be provided.
- If you have any doubt regarding the suitability of use, refer to Nippon Paint for further advice.

**DISCLAIMER**

The information in this data sheet is given to the best of Nippon Paint’s knowledge and practical experience. Users may consult with Nippon Paint on the general suitability of the product for their needs and specific application practices though it remains each user’s responsibility to determine the suitability of the product for the user’s particular use. The condition of the substrate and application are not within Nippon Paint’s control. Therefore no implied conditions, warranties or other terms will apply to the Product. Nippon Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will Nippon Paint be liable to the user for any kind of loss (whether direct or indirect) even if Nippon Paint was previously advised of it. In line with Nippon Paint’s policy for continuous development, Nippon Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user’s responsibility to check with Nippon Paint for the latest version of this data sheet. This data sheet has been translated into various languages. In the event of any inconsistency, the English version shall prevail.