

TECHNICAL DATA SHEET FOR

FLOOR-PRO 318 SF EPOXY ANTI-SLIP CLEAR

FLOOR-PRO 318 SF EPOXY ANTI-SLIP CLEAR is a two-component, 100% solid anti-slip clear coating formulated with premium grade epoxy coating system with enhanced adhesion on many substrate

FEATURES

- Solvent-free, low odour
- Does not affect appearance and losing the inherent original design of decorative elements or tiles
- Good balance of abrasion resistance, anti-slip and cleanability with anti-slip polymer
- 100% solid pure resin gives higher crosslinking for improved mechanical and chemical resistance
- Seamless

APPLICATION AREAS

- Used as an abrasion resistance and non-skid clear top coat on organic and inorganic substrate
- It has excellent adhesion on substrates such as glazed tiles, glass, wood, steel and also on concrete
- It is specifically designed as an anti-slip top coat on car parking deck, decorative tiles, washroom flooring, wet production and storage floor and walkway system

PHYSICAL PROPERTIES

Chemical Composition	Solvent-free epoxy
Colour	Clear
Finish	Gloss, Satin & Matt
Density, mixed	1.1 g/cm ³ @ 30°C
Viscosity, mixed	1000 - 2000 cps @ 30°C
Solid Content, mixed	100 % (By weight)

PERFORMANCE DATA

Adhesive strength	>1.5 N/mm ² (Concrete failure)
Taber Abraser Wear Index	30 mg / 1000 revolutions / 1 Kg (ASTM D 4060-10)
Light fastness (Scale 1-8, 8=best)	6 (DIN EN ISO 105-B02)

*Conditions such as installation process, inappropriate maintenance, short and long-term wear and use as well as surface contaminants (wet or dry) affects the slipperiness of flooring materials. To meet slip resistance requirement for wet conditions and/or surface contaminants (wet or dry), appropriate textured or anti-slip floor systems are recommended. Please contact Nippon Paint for further details and specifications.

**The final floor finish shall follow the profile of the concrete, therefore appropriate levelling compound is recommended to treat the undulating surface.

APPLICATION GUIDE

Mixing Ratio (by weight)	Gloss Level	Part A	: Part B
	Gloss	3.775	: 1.225
	Satin	3.800	: 1.200
	Matt	3.800	: 1.200
Number of coats	1 -2 coats		
Recommended Thickness			
Theoretical Coverage	0.1 – 0.15 Kg/m ² / coat		
Recoating time	Within 48 hrs @ 28°C		
Pot Life (Working time)	45 mins @ 28°C		

Curing time	30°C
	Foot traffic (hrs) 18
	Light traffic (days) 3
	Exposure to chemicals (days) 7
Substrate Temperature relative to dew point	≥ 3°C
Recommended application temperature range	Minimum 15°C Maximum 35°C
Relative Humidity	< 85%

SUBSTRATE REQUIREMENT

- Concrete or screed substrate should be a minimum of 25 N/mm² and adhesive pull off strength of 1.5 N/mm², free from laitance, dust and other contamination.
- The substrate should be dried up to 85% RH as per BS8204 and free from rising damp and ground water pressure.

SURFACE PREPARATION

- Concrete substrate must be clean, free of laitance and contaminants.
- The concrete substrate must be dry and waterproofed against negative ground water pressure.
- Appropriate moisture barrier at 2 mm thickness is recommended if the substrate moisture > 4%.
- In the event of high substrate moisture > 6%, it is recommended to apply a 5 mm thickness high compressive strength anti-osmosis epoxy mortar as moisture tolerance system.
- Allow to cure over-night before the application of subsequent painting system. Prepare the concrete substrate surface by captive shot blasting, scarifying or mechanical grinding. Repair damaged area and patch up cracks and holes using a patching compound. Cut 5mmX5mm grooves around the perimeter of the floor and at end points (eg: plinth, column, drains etc.)

APPLICATION METHOD

- The products in the system are multi-components and pre-packed in sets. Each set requires effective and homogenous mixing using drill and helical spinner with the least inclusion of air in a clean mixing barrel prior to applying.
- FLOOR-PRO 318 SF EPOXY ANTI-SLIP CLEAR is proportioned 2 component products which are spread on the floor by squeegee and finished with roller
- If reworking within 24/36 hours after application the coating need not be sanded. Reworking later than that is only possible after sanding it carefully.

PACKAGING

Components	Gloss Level	PART A (BASE)	PART B (HARDENER)
TOTAL 5 Kg	GLOSS	3.775	1.225
TOTAL 5 Kg	SATIN	3.800	1.200
TOTAL 5 Kg	MATT	3.800	1.200

STORAGE AND SHELF LIFE

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care. (Unopened and in good condition temperature 10°C to 30°C)

Components	PART A (BASE)	PART B (HARDENER)
Months	12	12

SAFETY PRECAUTION

- This product is intended for use by professional applicators. Refer to the safety information display on the container and in the safety data sheet (SDS) before using the product.
- Use this product in well-ventilated area, avoid skin contact, spillage on the skin should immediately be removed with suitable cleanser, soap and water.
- Eye should be well flushed with water and seek for medical attention immediately upon contact with this product.
- During the application, naked flame, welding operation and smoking is not allowed. Adequate ventilation should be provided.
- If you have any doubt regarding the suitability of use, refer to Nippon Paint for further advice.

DISCLAIMER

The information in this data sheet is given to the best of Nippon Paint’s knowledge and practical experience. Users may consult with Nippon Paint on the general suitability of the product for their needs and specific application practices though it remains each user’s responsibility to determine the suitability of the product for the user’s particular use. The condition of the substrate and application are not within Nippon Paint’s control. Therefore no implied conditions, warranties or other terms will apply to the Product. Nippon Paint does not and cannot warrant the results which the user may obtain by using the product. In no event will Nippon Paint be liable to the user for any kind of loss (whether direct or indirect) even if Nippon Paint was previously advised of it. In line with Nippon Paint’s policy for continuous development, Nippon Paint reserves the right to modify the product and the information in this data sheet without prior notice. It is the user’s responsibility to check with Nippon Paint for the latest version of this data sheet. This data sheet has been translated into various languages. In the event of any inconsistency, the English version shall prevail.