



**NIPPON
PAINT**

HI-FLORO 6738

FLUOROCARBON TOP COAT



Hi-Floro 6738

Fluorocarbon Top Coat

is a two-component, fast drying, fluorocarbon topcoat.

Features

This coating has excellent film stability, good contamination, chemical and weathering resistance and easy application.

Benefits

It provides long-term protection against weathering and contamination.

Applications

Hi-Floro 6738 Fluorocarbon Top Coat is ideal for structures such as bridges, petrochemical plant equipment, power generators, steel structures and other steelwork.

General Properties

Colour	: Colour range based on assortment list
Gloss Level	: Semi-Gloss
Volume Solids, %	: 46 ± 2 %
Specific Gravity	: 1.20 ± 0.15 kg/L (Mixed) - depending on colours
Flash Point	: Base: 13.3°C Hardener: 24°C Mix: 13.3°C
VOC	: 480 g/L (mix, by calculation)
Typical Thickness	: 40 - 60 µm dry film : 87 - 130 µm wet film

Notes:

All representations and statements concerning the product(s) in this brochure are accurate to the best of our knowledge, at the time of publication. Statements made in this brochure are advisory only and are not intended to be specific recommendations or warranties of any product, combination of products or fitness for any particular purpose, to the extent permitted by law, we do not accept any liability to any person for any loss or damage (direct or indirect) that may arise from any use of or reliance on any of the methods or information contained in this brochure for any purpose. Unless otherwise agreed in writing, all products supplied and technical advice or recommendations given are subject to the Conditions of Sale of our company. Any warranties, if given, are contained in those standard Conditions of Sale and are the only ones made with respect to any products we sell to you or advice or recommendations we give to you. For each of our products the relevant product Data Sheet, Material Safety Data Sheet and package labelling comprise an integral information system about the product in question. Copies of our product Data Sheets and Material Safety Data Sheets are available on request or from our website: www.nipponpaint.com.sg/trade