



**NIPPON
PAINT**

HI-PON 300 HT

TOP COAT



Hi-Pon 300 HT

Top Coat

Hi-Pon 300 HT Top Coat is a one-pack, silicone acrylic-based coating. It delivers long-term protection against corrosion for steel that is exposed to dry heat temperatures of up to 300°C.

Intended Use

It is suitable for use in exhaust manifolds, furnaces, boiler, chimneys and other installations exposed to high temperatures of up to 300°C.

General Properties

Colour	: Aluminium, Black and Red (up to 300°C) White (up to 260°C)
Gloss Level	: Semi-gloss
Volume Solid	: 40 ± 2 %
Specific Gravity	: 1.10 ± 0.10 kg/L – depending on colours
Flash Point	: 7°C
VOC	: 520 g/L (EPA Method 24)
Typical Thickness	: 20 – 30 µm dry film : 50 – 75 µm wet film

Notes:

All representations and statements concerning the product(s) in this brochure are accurate to the best of our knowledge, at the time of publication. Statements made in this brochure are advisory only and are not intended to be specific recommendations or warranties of any product, combination of products or fitness for any particular purpose, to the extent permitted by law, we do not accept any liability to any person for any loss or damage (direct or indirect) that may arise from any use of or reliance on any of the methods or information contained in this brochure for any purpose. Unless otherwise agreed in writing, all products supplied and technical advice or recommendations given are subject to the Conditions of Sale of our company. Any warranties, if given, are contained in those standard Conditions of Sale and are the only ones made with respect to any products we sell to you or advice or recommendations we give to you. For each of our products the relevant product Data Sheet, Material Safety Data Sheet and package labelling comprise an integral information system about the product in question. Copies of our product Data Sheets and Material Safety Data Sheets are available on request or from our website: www.nipponpaint.com.sg/trade