

TECHNICAL DATA SHEET FOR

QD RED OXIDE METAL PRIMER

DESCRIPTION	:	QD Red Oxide Metal Primer is an one-component quick dry alkyd-based shop primer for the protection of metals under mildly corrosive conditions
TYPE	:	Solvent-based alkyd resin primer
COLOUR	:	Iron Oxide Red
FINISH	:	Matt
USES	:	Specially developed as a quick drying shop primer for pipes, equipment, machinery and steel structures under normal conditions
FEATURES	:	<ul style="list-style-type: none">• Ready-to-use and fast dry• Good protection of suitably-cleaned metals under mildly corrosive environments• Good workability

APPLICATION DATA

METHOD	:	Roller, brush or spray
THEORETICAL COVERAGE	:	Approx 15 m ² / litre (based on 25 microns DFT per coat)
DILUTION	:	Ready to use. If needed, dilute 5 - 10% using Bodelac 9000 GP Reducer
SURFACE PREPARATION	:	Ferrous Metal Surface: Remove rust and any unstable matter by power brushing or sand paper. The surface must be clean and dry, free from grease, oil, rust and other foreign matter. For optimum performance, abrasive blasting to Sa 2½ ISO 8501-1:1998 is recommended Non-Ferrous Metal Surface: Clean and remove any oil or grease and other forms of dirt or light rust. For optimum performance, prime exposed bare metal surface with a coat of Vinilex 120 Active Primer
DRYING TIME	:	Surface Dry - 10 minutes at 30°C Hard Dry - 30 minutes at 30°C

QD RED OXIDE METAL PRIMER

OVERCOATING TIME : 30 minutes based on normal conditions

POT LIFE : Not applicable

CLEANING : All equipment should be cleaned with Bodelac 9000 GP Reducer immediately after use

GENERAL INFORMATION

SOLID CONTENT : 70.0 ± 2 % by weight

SPECIFIC GRAVITY : 1.45 ± 2 % kg/litre

Flash Point : 7 °C

PACKING : 20 litres

STORAGE : Store in a tightly sealed container in a cool dry place

SHELF LIFE : Up to 24 months in a tightly sealed container

PRECAUTION : Ensure good ventilation during application and drying of paint. Avoid direct contact with sensitive skin. Use appropriate personal protective equipment.

Refer to the product Safety Data Sheet for more information

The information given is intended to give a description of the product performance under specific test conditions. Nevertheless, we cannot assume any responsibility for the use of it since circumstances under which the products are applied in practice are subjected to many variations. We reserve the right to alter the given data without notice.

Enquiries / Contact Details : **Customer Service**
6265 5355 (Main Line)
6264 1603 (Fax)
www.nipponpaint.com.sg