

TECHNICAL DATA SHEET FOR

SOLAREFLECT COOLFLOOR PRIMER

DESCRIPTION	:	SolaReflect CoolFloor Primer is a two component water-based Acrylic Epoxy Hybrid (AEH) penetrative primer. It is formulated to enhance the adhesion of subsequent mid and topcoats over pavement, asphalt, and concrete surfaces.
TYPE	:	2 component water-based Acrylic Epoxy Hybrid (AEH) penetrative primer
COLOUR	:	Clear
FINISH	:	Semi-gloss
USES	:	Specially formulated primer for the following surfaces: <ul style="list-style-type: none">• New and existing pavement, asphalt, and concrete surfaces
FEATURES	:	<ul style="list-style-type: none">• Excellent penetration power into porous substrates such as asphalt, pavement, concrete and cement, thus providing a good base for subsequent coats• Outstanding alkaline resistance• Anti-fungus and anti-algae properties• Fast drying• Long pot life• Easy application• Low odour

APPLICATION DATA

METHOD	:	Roller or brush
THEORETICAL COVERAGE	:	On concrete: 0.1 ~ 0.3 Kg / m ² at dry film thickness of 50 µm per coat On asphalt & pavement: 0.4 ~ 0.6 Kg / m ² at dry film thickness of 50 µm per coat
DILUTION	:	No dilution is necessary for best performance
MIXING RATIO	:	Part A : Part B = 4:1 (by weight)
POT LIFE	:	4 Hrs at 25 °C

Important note: Do not use mixed materials beyond the recommended pot-life of 4 hours. As Part B is sensitive to the weather, only open the Hardener (Part B) portion when required for mixing and close tightly after use

SOLAREFLECT COOLFLOOR PRIMER

- SURFACE PREPARATION** : Ensure surface is clean, dry and stable using the following suggested surface treatments:
- **Moisture:** There must not be any water residue on the surface of the substrate. Moisture must be <4% (Tramex CME4 moisture master) before application
 - **Unstable matter:** Remove loose bonding film, dirt, peeling paint, etc by high-pressure water jet wash or mechanical means such as grinding, sanding, scarifying, power brush or scraper, whichever is suitable
 - **Contaminants:** Remove dust and foreign matter by cleaning with damp cloth. Remove oil or grease using solvent or mild detergent. Allow surface to dry
 - **Fungus and Algae:** Wash the affected area to remove unstable matters and micro-organisms. Apply Anti-Fungus Solution and leave on for at least 2 hours
 - **Undulated Substrate:** Levelling with FLOORSHIELD SF EPOXY MORTAR or FLOORSHIELD 831 RE-SURFACING SCREED or any compatible levelling compound to achieve the desired flatness
- DIRECTION OF USE** : **Mixing**
Stir each component separately using an electric drill fitted with a paint mixer or a wing type mixing paddle. Pour the entire contents of Part B into Part A while stirring and mix evenly for approximately 5 minutes until a homogenous tone is achieved.
- Important note: Do not attempt to mix both component manually, mechanical stirrer must be used to assure the effective mixing**
- DRYING TIME** : Touch Dry – 30 mins at 30 °C
Hard Dry – 2 hours at 30 °C
- OVERCOATING TIME** : 2 hours minimum at 30 °C
- RECOMMENDED PAINTING SYSTEM** :
- Primer: 1 coat of SolaReflect CoolFloor Primer
 - Midcoat: 1 coat of SolaReflect CoolFloor Midcoat
 - Non-skid aggregate
 - Topcoat: 2 coats SolaReflect CoolFloor Topcoat
- CLEANING** : All equipments should be cleaned with water immediately after use

SOLAREFLECT COOLFLOOR PRIMER**GENERAL INFORMATION****SOLID CONTENT** : 51.0 ± 2.0 % by weight (mixture)**SPECIFIC GRAVITY** : 1.07 ± 2.0 % kg / litre (mixture)

PACKING	Unit	Part A		Part B	
		Weight	Container Size	Weight	Container Size
		20 KG	16 KG	20 L	4 KG
	5 KG	4KG	5 L	1 KG	1 L

STORAGE : Store in a tightly sealed container in a cool, dry place**SHELF LIFE** : Up to 12 months in a tightly sealed container**PRECAUTION** : Ensure good ventilation during application and drying of paint. Avoid direct contact with sensitive skin. Use appropriate personal protective equipment

Refer to the product Safety Data Sheet for more information

The information given is intended to give a description of the product performance under specific test conditions. Nevertheless, we cannot assume any responsibility for the use of it since circumstances under which the products are applied in practice are subject to many variations. We reserve the right to alter the given data without notice.

Enquiries / Contact Details : **Customer Service**
6265 5355 (Main Line)
6264 1603 (Fax)
www.nipponpaint.com.sg