



TEST REPORT

Daylight Reflectance

Ref: Test Result/TR-Color-193
Established: 05-April-17
Updated: --

Background:

% Daylight Reflectance = % Diffuse Reflectance + % Specular Reflectance

Daylight Reflectance: Specular reflectance included (SCI) is the measurement of the total or daylight reflectance from a surface that including the diffuse and specular reflectance

Diffuse Reflectance: Specular reflectance excluded (SCE) is the measurement of reflectance made with specular reflectance excluded from the measurement.

Definition:

Specular Reflection is the mirror-liked reflection of a beam of light from a surface, in which the beam from a single incoming direction is reflected into a single outgoing direction

Diffused Reflection refer to the single light beam falls onto a rough surface, the ray of light will be reflected in different directions.

Objective:

To measure the daylight reflectance value of color.

Method:

The method of measurement is with reference to ASTM E903-12: Standard Test Method for Solar Absorptance, Reflectance and Transmittance of Materials.

Instrument used is the X-rite Color Eye CE 7000A spectrophotometer with the following parameters:

1. Measurement Geometry Angle: 8 degree
2. Integrating sphere size: 6" (15.2 cm) integrating sphere
3. Wavelength: 360-750nm
4. Illuminant: D65

**Disclaimer: Daylight reflectance is measured using Color Card.*

NIPPON PAINT (SINGAPORE) CO PTE LTD

1, First Lok Yang Road, Jurong, Singapore 629728. Tel: 6265 5355 Fax: 6264 1603

Co Reg No. 196200138N

www.nipponpaint.com.sg

A MEMBER OF THE NIPSEA GROUP



TEST REPORT

S/N	Color	% Daylight reflectance	% Diffuse reflectance	% Specular reflectance
1	CTL Aluminum Paint	68.35	63.44	4.91

NIPPON PAINT (SINGAPORE) CO PTE LTD

1, First Lok Yang Road, Jurong, Singapore 629728. Tel: 6265 5355 Fax: 6264 1603

Co Reg No. 196200138N

www.nipponpaint.com.sg

A MEMBER OF THE NIPSEA GROUP