

TECHNICAL DATA SHEET FOR

WOODGUARD

DESCRIPTION	:	WoodGuard is an air-drying type of polyurethane which does not require any addition of hardener. It dries quickly to a glossy, durable finish while enhancing the character of the natural grains of wood. With its enhanced UV protection property and flexibility, the varnish protects timber surfaces from the damaging effects of UV rays, making it ideal for exterior deck and outdoor furniture
TYPE	:	One pack solvent-based polyurethane modified alkyd paint for interior and exterior use
COLOUR	:	Transparent colours as per colour card
FINISH	:	Gloss
USES	:	Suitable for all types of new wood surfaces and those previously painted with a transparent wood film such as stair railing, fences, door, frame, furniture, parquet flooring and deck etc
FEATURES	:	<ul style="list-style-type: none">• Excellent UV and weather resistance• Excellent water repellency• Excellent dirt resistance• Flexible finish• Desirable scratch hardness• Excellent flow and leveling• Good resistance to fungus and mould• Easy to apply

APPLICATION DATA

METHOD	:	Brush
THEORETICAL COVERAGE	:	Approximately 10 to 15 m ² /litre, depending on surface porosity
DILUTION	:	Ready for use, if necessary, dilution of not more than 5% with General Purpose Thinner
SURFACE PREPARATION	:	<ul style="list-style-type: none">• New or unpainted wood surfaces :<ol style="list-style-type: none">a) Surface must be clean, dry and free from grease, paint, wax, dirt and other contaminants before paintingb) Clean off mould, algae, lichen and moss with a wire brushc) Smooth bare wood surface to be painted using grade #60 or #80 sandpaper, working in the direction of the grain before dusting off

WOODGUARD

- d) If necessary, fill the wood grains with appropriate filler and smooth with sandpaper (grade #150 or #180)
- e) Wood must be relatively dry and moisture content should not exceed 20% based on Sovereign Moisture Master before painting
- f) Allow the paint to dry thoroughly before applying next coat
- g) Should fibre be observed, dry sand lightly before subsequent coat

Sanding between individual coats is necessary. Use grade #360 or #400 for sanding topcoat

- **Previously Painted Wood Surfaces :**

- a) If the previous paint film is in sound condition and without wax, smoothen it with sandpaper. Clean off and dry
- b) For old paint which is in sound condition and without wax, smoothen it with sandpaper. Clean off and dry
- c) Otherwise, remove all unstable paint film, dust, oil, wax and other foreign matters
- d) Particular care is necessary on previously waxed surfaces and thorough mechanical sanding is recommended to remove all wax. Presence of wax on substrates will affect the drying and adhesion of the paint coating

DRYING TIME	: Touch dry: 1 hour at 30°C
OVERCOATING TIME	: Minimum 4 hours under normal conditions
RECOMMENDED PAINTING SYSTEM	: 2 to 3 coats of WoodGuard until a satisfactory wood finish is obtained
CLEANING	: Wash all equipment with Bodelac 9000 General Purpose Reducer
GENERAL INFORMATION	
SOLID CONTENT	: 50.0 ± 2% by weight (average, varies from colour to colour)
SPECIFIC GRAVITY	: 0.90 ± 2% kg/litre (average, varies from colour to colour)
PACKING	: 1 litre and 5 litres
STORAGE	: Store in a tightly sealed container in a cool, dry place
SHELF LIFE	: Up to 24 months in a tightly sealed container
PRECAUTION	: Ensure good ventilation during application and drying of paint. Avoid direct contact with sensitive skin. Use appropriate personal protective equipment

Refer to the product Safety Data Sheet for more information

WOODGUARD

The information given is intended to give a description of the product performance under specific test conditions. Nevertheless, we cannot assume any responsibility for the use of it since circumstances under which the products are applied in practice are subjected to many variations. We reserve the right to alter the given data without notice.

Enquiries / Contact Details : **Customer Service**
6265 5355 (Main Line)
6264 1603 (Fax)
www.nipponpaint.com.sg