



TECHNICAL DATA SHEET FOR

QUICK DRY QD UNDERCOAT

DESCRIPTION : Quick Dry QD Undercoat is a high solid quick drying coating with

superior opacity that effectively hides the substrate and imparts a good film build to the overall coating system. Widely used as an

undercoat over timber and metal.

TYPE : Oil-modified alkyd

COLOUR : White

FINISH : Matt

USES : Specially designed undercoat for appropriately primed metals and

woods.

FEATURES : • Fast drying

Good opacity for easy coveragePromote good intercoat adhesion

APPLICATION DATA

METHOD : Roller, brush or spray

THEORETICAL COVERAGE: Approx 18 m² / litre (for DFT of 30 microns)

DILUTION : Use Bodelac 9000 GP Reducer

Roller & brush : 5 - 10%Air spray: 5 - 20%

SURFACE PREPARATION : Metal

For optimum performance, abrasive blast to Sa 2½ or power tool cleaning to min. St2 (ISO 8501-1:1988 standard) for steel substrates

may be acceptable, subjected to exposure condition.

Wood

Prepare by sanding to establish a smooth clean surface.

DRYING TIME : Surface Dry - 20 minutes at 30°C

Hard Dry - 2 hours at 30°C

OVERCOATING TIME : Minimum 2 hours based on normal conditions

TECHNICAL DATA SHEET FOR

QUICK DRY QD UNDERCOAT

RECOMMENDED PAINTING

SYSTEM

Recommended primer for the following substrates:

Ferrous metal - Crystalux A/C Primer

Non-ferrous metal - Nippenyl 6052 Wash Primer

Timber - Bodelac 9000 Aluminium Wood Primer

CLEANING : All equipment should be cleaned with Bodelac 9000 GP Reducer

immediately after use.

GENERAL INFORMATION

SOLID CONTENT : $55 \pm 2\%$ by volume

SPECIFIC GRAVITY : $1.60 \pm 2\%$ kg / litre

NO. OF COMPONENTS : 1

MIXING RATIO : N/A

POT LIFE : N/A

FLASH POINT : 41°C

PACKING : 1 and 5 litres

STORAGE : Store in a tightly sealed container in a cool dry place.

SHELF LIFE : Up to 24 months in a tightly sealed container.

PRECAUTION : Ensure good ventilation during application and drying of paint. Avoid

direct contact with sensitive skin. Use appropriate personal protective

equipment

Refer to the product Safety Data Sheet for more information.

The information given is intended to give a description of the product performance under specific test conditions. Nevertheless, we cannot assume any responsibility for the use of it since circumstances under which the products are applied in practice are subjected to many variations. We reserve the right to alter the given data without notice.

Enquiries / Contact Details : Customer Service

6265 5355 (Main Line) 6264 1603 (Fax)

www.nipponpaint.com.sg